



# KonFusion Chameleon Effect Paints

## Description

KonFusion™ Color Change basecoats are a combination of highly weatherable urethane reactants, premium solvents, U.V. additives and the latest in color changing pearl technology. Our urethane basecoats spray easily, cover fast, lay down smooth, and dry quickly to a durable long lasting finish once properly clear coated. Unique technology changes between 2-5 hues depending on the angle you view them and lighting conditions. Apply over dark base (black gives most color change) for spectacular color shift. Check local regulations for compliance before using.



## Colors




<b>KF-01</b>	Nature's Fury	<b>KF-06</b>	Mountain Fall
<b>KF-02</b>	Storm Surge	<b>KF-07</b>	Hole Shot
<b>KF-03</b>	Ocean's Rip	<b>KF-08</b>	Tokyo Drift
<b>KF-04</b>	Tropical Storm	<b>KF-09</b>	Psychotic Illusions
<b>KF-05</b>	Toxic Tide	<b>KF-10</b>	Nuclear Gold

## Suitable Substrates



Apply over UreKem 2K urethane primer, sealer, or kembase basecoat after proper flash times. Not recommended for direct use over epoxy or enamel primers. For best color change apply over dark bases such as our SGCB000 BlackOut Black Base. Other colors may be used to give varying color shift effects.

## Mix Ratio



For spray applications mix 2 parts KonFusion base with 1 part Urekem UR-010 (fast), UR-011 (medium) or UR-012 (slow) reducer by volume. While not required, 2 ounces of UA series activator per sprayable quart is recommended for enhanced durability. Additional reduction may be required for use in an air brush application. Mix gently then strain before use.

## Application



Apply 3-5 medium coats using 75% overlap at a gun distance of 6-8 inches. HVLP or reduced pressure (RP) guns should be equipped with 1.2-1.5 mm tips and generally set for 24-32 psi standard HVLP or 12-18 psi for RP guns. Avoid heavy or very light coats so as to ensure good orientation. When painting sides of vehicles walk the entire length of the vehicle spraying before then overlapping 75% (approximately a 2 inch movement of your previous spray) and spraying all the way back down the to the other end of the vehicle side. Do not paint one quarter panel at a time to avoid light streaks where you overlap. Allow to flash 10-15 minutes between coats. After final coat application allow to flash at least 30 minutes but no more than 24 hours before application of a UreKem 2K polyurethane clear. Always prepare a test panel to verify gun settings, effect, and desired color before painting your object.

Read MSDS of all components before using. Use proper personal protective equipment at all times. For use by professionally trained painters. **KEEP OUT OF REACH OF CHILDREN.** Bayou Innovations, LLC warrants that its products are free from defects at time of shipping. All other warranties and guaranties of any kind whether expressed or implied are disclaimed.