



# EyeKandy 2K Urethane Kandy Color

*EKU Series*

## Description

The "EKU" series candy colors are the combination of our true EyeKandy dyes and pigments with gloss, 2K urethane topcoat chemistry to provide candy colors that provide greater depth and gloss for a maximum "wet look". This series candy is best suited for overall painting where maximum candy effect desired. The EKU series has the best longevity of the candy series of colors. However, use of a high solids, UreChem clear and storage inside or under a UV protected cover when not in use is recommended for best longevity.



## Safety

Read all SDS, and label warnings before using this product. For professionally trained painters using proper personal protective equipment. When mixed with other products this product will have hazards of all components. Keep away from extreme heat, sparks, open flames or any other potential ignition sources. Wear all personal protective equipment including the recommended respirator, gloves, and protective eyewear at all times including when opening, mixing/pouring, and applying material. When mixed for use this product contains isocyanates. Persons who have experienced reactions or sensitivity to isocyanates should not use or be exposed to this product. **KEEP OUT OF REACH OF CHILDREN.** In case of chemical or medical emergency call ChemTel 24/7 at 1-800-255-3924 and/or 911.




## Components

<b>EKU Series Color</b>	<i>Transparent EyeKandy 2K Urethane Midcoat</i>
<b>UR Series Reducer</b>	<i>UreChem Fast, Medium or Slow Reducer</i>
<b>UA Series Activator</b>	<i>UreChem Fast, Medium, or Slow Urethane Activator</i>



## Substrates/Undercoats

Apply over UreChem basecoat after proper flash time. The final color and depth of EyeKandy finishes is dependent on the color of the base chosen and the thickness of coats applied. Metallic basecoat colors are commonly used but pearl and solid color basecoats may also be used if less or no sparkle effect is desired.



## Mixing Instructions

For spray applications mix 4 parts EKU series midcoat with 1 part UA series UreChem activator and 1 part UA Series reducer by volume. Additional reduction may be required for use in an air brush application. Mix gently then strain before use.





# EyeKandy 2K Urethane Kandy Color

*EKU Series*



## Additives

See mixing instructions for main component mix ratios. If fish eyes are observed a 1/2 ounce per sprayable quart of AFE-52 may be used. For flexible parts applications 20% by volume QF-777 QuadFlex adhesion promoter may be added for enhanced flexibility.



## Application/Suggested Gun Settings

Apply 2-4 medium to medium wet coats using 75% overlap at a gun distance of 6-10 inches. Guns should be equipped with 1.2-1.4 mm tips and set for 40-55 PSI for conventional guns or 22-30 psi (trigger pulled) for HVLP. Allow to flash 15 minutes between coats. Fluid settings of 2-3 turns out from "hand tight" are a good starting point. Gun settings are suggested starting points and adjustments to your specific equipment and spray style are often required. Spray test panels to check effect and adjust as needed.



## Flash/Dry Times @ 75F

Flash Between Coats	.....	15 minutes
Dry to nib sand	.....	2 hours (must be very light and small area)
Dry to tape/topcoat/clearcoat	.....	???
Maximum time till clearcoat	.....	???



## Cleanup

Clean equipment immediately after use. UreChem urethane reducer, lacquer thinner or acetone are commonly used cleaners that are suitable for cleaning up after this product. Check local regulations to ensure compliance.



## Select Tips/Best Practices

- Do not apply if dew, fog, or rain is present outside or will be shortly after spraying
- Apply coats evenly to avoid light and dark areas. For overall painting it is best to "walk" the length of the vehicle with each pass to ensure uniformity from front to back (ie panel painting may lead to dark stripes in overlap areas where panels meet.
- Install and maintain water/moisture reducing traps and filters in your air systems
- If you have more than one can of paint bought at separate times blend all cans together to minimize variations from lot to lot.
- Make sure your shop air is able to provide at least 25% more CFM than equipment specifies

The descriptions, recommendations, and data presented herein are provided for your guidance to the best of our ability. No warranties of an kind, either expressed or implied, including warranties for merchantability or fitness for a particular purpose are made regarding these products unless otherwise provided in writing and signed for by an officer of Bayou Innovations, LLC. Bayou Innovations, LLC assumes no obligation or risk or liability for use as directed herein or otherwise.